



# Laminated Glass PVB .030

## Performance Data

Interlayer Color	Glass Type	Thickness	Visible Light Transmission	Solar Transmission	Light to Solar Gain
Clear	Clear	1/4"	88%	72%	1.11
Clear	Clear	3/8"	87%	69%	1.14
Clear	Clear	1/2"	87%	67%	1.16
Clear	Low iron	1/4"	91%	83%	1.07
Clear	Low iron	3/8"	91%	82%	1.08
Clear	Low iron	1/2"	91%	81%	1.08
Arctic White	Clear	1/4"	65%	57%	.96
Arctic White	Clear	3/8"	63%	49%	1.00
Arctic White	Clear	1/2"	62%	46%	1.02
Polar white	Clear	1/4"	6%	3%	.55
Polar white	Clear	3/8"	5%	2%	.45
Polar white	Clear	1/2"	4%	2%	.33
Green	Clear	1/4"	72%	62%	1.00
Green	Clear	3/8"	71%	56%	1.06
Green	Clear	1/2"	69%	53%	1.06
Bronze	Clear	1/4"	52%	49%	1.05
Bronze	Clear	3/8"	51%	44%	.81
Bronze	Clear	1/2"	47%	39%	.85
Grey	Clear	1/4"	43%	47%	.82
Grey	Clear	3/8"	43%	42%	.69
Grey	Clear	1/2"	42%	40%	.74

Actual values may vary due to the production process and manufacturing tolerances.

## Contact us to learn more.

800-431-2042 | [sales@generalglass.com](mailto:sales@generalglass.com) | [www.generalglass.com](http://www.generalglass.com)

SEE WHAT  
**GLASS**  
CAN DO