

Technical Data

Clear and Low Iron Satin Etched

Glass Substrate	Thickness [mm]	Light Transmittance [%]
Clear	4.0	85.6
Clear	6.0	85.3
Clear	8.0	84.8
Clear	10.0	84.2
Clear	12.0	84.6
Low Iron	4.0	87.4
Low Iron	6.0	86.0
Low Iron	8.0	86.5
Low Iron	10.0	86.4
Low Iron	12.0	86.3

Glass Substrate	Gloss [GU]	Clarity [%]	Haze [%]
Clear	10-15	6-10	90-95
Low Iron	10-15	6-10	90-95

- Measurements made on 3210 x 2250 mm glass sheet.
- Measurement results may vary by +/- 10% on the glass sheet.

Terminology:

Gloss: The gloss of a surface is described as the reflection of light from the surface that is independent of color.

Haze: Haze is the scattering of light as it passes through a transparent material.

Transmittance: Transmittance is the amount of light that passes through glass.

Contact us to learn more.

800-431-2042 | sales@generalglass.com | www.generalglass.com